



GF Oil Base Wood Stain



The industry leader in water based technology.

Classification:

Oil Based Stain

Product Description:

General Finishes Oil Base Wood Stains are considered the standard in the industry. Produced from the highest quality oils, resins, and pigments, our Oil Base Wood Stains produce deep, rich colors demanded by today's quality standards. These wiping stains penetrate deeply into the grain of the wood. Once dry, they may be topcoated with oil, water, or solvent-based finishes, varnishes, or lacquers. General Finishes Oil Base Wood Stains are available in a variety of stock colors, and may be tinted to match your specific needs. They provide plenty of open time for wiping, and are formulated for low odor and easy clean-up.

Application:

Apply via applicator, wiping cloth, brush or spray. Stir well before application. Apply liberal amount of stain to the surface and allow to penetrate several minutes. Wipe off stain evenly with a clean, dry cloth. A second coat may be applied to darken the color. Allow 6 -72 hours dry before topcoating.

Product Data:

- Density: 6.9 – 8.9 lbs. / gal
- Weight Solids: 36 - 43% (color dependant)
- Volume Solids: 28 - 30%
- Viscosity: 18 - 35 seconds
- Method: #4 Ford
- pH: NA
- V.O.C.: <550 g/l (4.59 lbs/gal)

- % VOC: 57 - 66%
- Coverage: Approx. 800 sq. ft. / gal

Container:

Pints, Quarts, Gallons, Fives and Drums

Sheen:

Not Applicable

Dry Time: 70°F and 70% R.H:

- Dry: 6 - 12 hours
- To Topcoat: 6 -72 hours

General Finishes, 2462 Corporate Circle, East Troy, WI 53120
800.783.6050 (F) 262.642.4707

www.generalfinishes.com

The industry leader in water based technology.

Mixing and Application:

- Catalyst Ratio: None
- Pot Life: Not Applicable
- Shelf Life: 1 year, minimum
- Reducer/Thinner: Mineral Spirits (10 -20%)

Sealer & Finish Recommendation:

Can be topcoated with most water base, oil base, and solvent base finishes, varnishes, & lacquers. Compatible with all General Finishes topcoats. Test adhesion and compatibility on all other systems.

For best results topcoat with General Finishes Arm-R-Seal in the desired sheen. May also topcoat with General Finishes Oil Base Gel Satin topcoat. General Finishes Oil Base Stain may also be topcoat with water base finishes if first evaluated for proper adhesion before proceeding. Allow a minimum of 72 hours dry before topcoating with water base topcoats.

Surface Preparation:

Surface must be clean, dry and free of dust, dirt, grease, wax, or contaminants. For soft woods, sand with #120 grit & finish with #150 -#180. For hard woods, sand with #100 grit & finish with #120. Fill all nail holes or cracks using a stain-accepting filler or putty. Remove all dust by vacuuming or wiping with a damp cloth. Do not use tack cloths which contain linseed oils.

Application:

- Conventional Spray
- Spray
- Brush
- Pad Applicator
- Clean wiping cloth

Cautions:

- Mix container before use
- Use with proper ventilation
- Read MSDS for safety information

Clean-up Information:

For best results, clean all equipment with Mineral Spirits.

GF Oil Base Stain-050211

NOTICE: All of the above statements, recommendations, suggestions, and data concerning the subject material are based on laboratory results and believed to be reliable. We expressly do not represent, warrant, or guarantee the accuracy, completeness or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like and (THE MANUFACTURER DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED,) OF MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE.
